

TITLE APPL Trial 81 Determine Dye and  $H_2O_2$ 

From Page No. —

Levels to Achieve Target L and b Values

## EXHIBIT A

## APPL Trial T-81

Project Manager: Scott Stephens (NGCF - New Generation Curly Fibers)  
 Project Number: 00050 W532 615 874 731 142-4513

## Objectives:

- Attempt to overcome dye-caused L loss by post-treatment with alkaline hydrogen peroxide.
- Determine combinations of low dye levels and peroxide that will simultaneously achieve target L and b values.
- Produce samples for customer evaluation

## Safety:

- Review MSDS's for all chemicals.
- Use proper personnel protective gear when handling the 50% hydrogen peroxide solution - goggles, face shield and rubber gloves. Other staff are to remain clear of this working area.
- Handle post-treatment solutions with care - prior to hydrogen peroxide addition, pH will be greater than 11.
- Use normal safety precautions related to working around the APPL area during its operation.

## Run Conditions:

Pulp	CF416
Pulp Linear Feed rate	60 fpm
Cross-linking Chemistry	CS-10
Impregnation Solution	See Run Matrices
Impregnation Solution pH	Adjust to pH between 2-2.1
Target Hammermill Feed Consistency	61%
Target Citric Acid on BDCF Pulp	7.616%
Target SHP (SHP.H <sub>2</sub> O Basis) on BDCF Pulp	0.683 %
Dye Types Evaluated	Pergasol Blue PTD
	Pergasol Blue NLF
	See Run Matrix
Dye Addition Rate	44.7 % of scale
Impregnation Solution Rotameter Setting	360 °F
Nominal Cure Temperature	5 minutes
Nominal Cure Time	8-9%
Target Product Moisture	See Run Matrix
Remoisturization Solutions	60% of scale reading (Water Pressure - 20 psi with air pressure
Remoisturization Rotameter Setting	adjusted to achieve this setting, approximately 27-28 psi.)

## Samples:

Pulp Feed Rolls: 2 samples per roll  
 Hammermill Feed: 3 samples per run condition  
 Baler Feed: 5 samples at steady state operation at least 2 minutes apart for each condition

In addition to the material bagged for analysis, collect and bag at least 1 kg of material at each condition for possible use as customer samples. Place samples in a black plastic bags for storage.

## Sample Analyzes:

Pulp Feed Rolls: Moisture  
 Hammermill Feed: Moisture  
 Baler Feed: Moisture, Brightness, Hunter and CIE Color (0 & 14 days), 5K and odor

- Baler Feed 5K, brightness and color samples will be placed in 13" x 18" bags. (These sample bags must not be exposed to light for any long term duration. Place all sample bags in a black plastic bag and store in the black plastic bag.)
- Pulp Feed Rolls, Hammermill Feed and Baler Feed moisture samples will be placed in 9x12 inch sample bags. Baler Feed moisture samples will e also used of odor determination.

Planning Summary T-081

1 OF 2

To Page No. 6

Witnessed &amp; Understood by me,

Date

Invented by

Date

Recorded by

Kathy Welch

BEST AVAILABLE COPY

From Page No. 35

## EXHIBIT B

Run Matrix						
Run ID	Impregnation Solution		Post-Treatment Targets		Post-Treatment Recipes	
	Dye Type	Dye Loading oz./ADMT	NaOH lbs./ADMT	Hydrogen Peroxide lbs./ADMT	Solution Recipes (per 22.7 lbs. of DI Water)	
					lbs. NaOH	mls H <sub>2</sub> O <sub>2</sub>
A (Control)	No dye	0	0	0	0.000	0.0
B (Control)	No dye	0	2	1	0.362	138.1
C (Control)	No dye	0	2	2	0.364	278.3
D (Control)	No dye	0	2	5	0.373	713.0
E	Blue PTD	1	0	0	0.359	0.0
F	Blue PTD	1	2	1	0.362	138.1
G	Blue PTD	1	2	2	0.364	278.3
H	Blue PTD	1	2	5	0.373	713.0
I	Blue PTD	2	0	0	0.000	0.0
J	Blue PTD	2	2	1	0.362	138.1
K	Blue PTD	2	2	2	0.364	278.3
L	Blue PTD	2	2	5	0.373	713.0
M (Control)	No dye	0	0	0	0.000	0.0
N (Control)	No dye	0	2	1	0.362	138.1
O (Control)	No dye	0	2	2	0.364	278.3
P (Control)	No dye	0	2	5	0.373	713.0
Q	Blue NLF	1	0	0	0.359	0.0
R	Blue NLF	1	2	1	0.362	138.1
S	Blue NLF	1	2	2	0.364	278.3
T	Blue NLF	1	2	5	0.373	713.0
U	Blue NLF	2	0	0	0.000	0.0
V	Blue NLF	2	2	1	0.362	138.1
W	Blue NLF	2	2	2	0.364	278.3
X	Blue NLF	2	2	5	0.373	713.0

## NOTES:

- DI water is to be used for post-treatment solution make-up
- Add the peroxide to the water just prior to dumping into the remoisturization tank to keep the peroxide as active as possible.

Impregnation Solution Recipes			
Dye Addition Rate	0	1	2
Solution Make-up Contingency Factor	52.0	52.6	52.6
Target Solution Component Weight in Pounds (Dye in grams)			
Citric Acid (as-received), lbs.	40.30	40.30	40.30
SHF (as-received), lbs.	3.61	3.61	3.61
Caustic (as-received), lbs.	0.96	0.96	0.96
Dye (Neat), grams	0.000	8.218	16.436
Water, lbs.	333.20	333.20	333.20
Total, lbs.	378.07	378.07	378.07
Volume of Water, gallons	40.0	40.0	40.0
Impregnation Solution Specific Gravity	1.05	1.05	1.05
Volume of Impregnation Solution, gallons	43.2	43.2	43.2

pH adjust all Cross-linking chemical solutions to 2-2.1

Discharge no chemical solutions until pH is adjusted to between 5 and 9. Record approximate quantity discharged and measured pH in the APPL Daily Log Book.

Planning Summary T-081

2 OF 2

BEST AVAILABLE COPY

Witnessed &amp; Understood by me,

Date

Invented by

Date

Recorded by

Kathy Welch

To Page No. 37

**TITLE**

ARPL Trial 81 (cont.)

From Page No. 44

# EXHIBIT C

## Test Results

### Absorbent Products Pilot Line - Trial # 81

[illegible]

**BEST AVAILABLE COPY**

To Page No. 46

**Witnessed & Understood by me,**

**Date****Invented by**

Date \_\_\_\_\_

Recorded by:

EXHIBIT D

Test Results

Absorbent Products Pilot Line - Trial # 81

Item	Material	7.616	0.683	44.7	None	0.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.21	61.00	95.00	0.165
61	M-1	7.616	0.683	44.7	None	0.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.21	61.00	95.00	0.165
62	M-2	7.616	0.683	44.7	None	0.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.21	61.00	93.03	0.150
63	M-3	7.616	0.683	44.7	None	0.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.21	61.00	93.60	0.148
64	M-4	7.616	0.683	44.7	None	0.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.21	61.00	94.10	0.162
65	M-5	7.616	0.683	44.7	None	0.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.21	61.00	90.67	0.150
66	N-1	7.616	0.683	44.7	None	0.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.21	60.69	92.97	0.143
67	N-2	7.616	0.683	44.7	None	0.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.21	60.69	93.97	0.158
68	N-3	7.616	0.683	44.7	None	0.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.21	60.69	92.50	0.148
69	N-4	7.616	0.683	44.7	None	0.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.21	60.69	95.40	0.143
70	N-5	7.616	0.683	44.7	None	0.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.21	60.69	90.27	0.137
71	Q-1	7.616	0.683	44.7	None	0.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.31	59.69	94.37	0.157
72	Q-2	7.616	0.683	44.7	None	0.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.31	59.69	93.50	0.151
73	Q-3	7.616	0.683	44.7	None	0.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.31	59.69	93.60	0.156
74	Q-4	7.616	0.683	44.7	None	0.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.31	59.69	93.60	0.158
75	Q-5	7.616	0.683	44.7	None	0.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.31	59.69	94.93	0.137
76	P-1	7.616	0.683	44.7	None	0.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.58	93.67	0.143
77	P-2	7.616	0.683	44.7	None	0.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.58	94.93	0.148
78	P-3	7.616	0.683	44.7	None	0.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.58	93.50	0.157
79	P-4	7.616	0.683	44.7	None	0.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.58	95.13	0.152
80	P-5	7.616	0.683	44.7	None	0.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.58	93.53	0.155
81	Q-1	7.616	0.683	44.7	Blue NLF	1.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.29	92.77	0.141
82	Q-2	7.616	0.683	44.7	Blue NLF	1.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.29	91.07	0.140
83	Q-3	7.616	0.683	44.7	Blue NLF	1.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.29	91.50	0.145
84	Q-4	7.616	0.683	44.7	Blue NLF	1.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.29	91.33	0.138
85	Q-5	7.616	0.683	44.7	Blue NLF	1.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.31	60.29	90.00	0.138
86	R-1	7.616	0.683	44.7	Blue NLF	1.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.06	92.17	0.135
87	R-2	7.616	0.683	44.7	Blue NLF	1.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.06	94.20	0.139
88	R-3	7.616	0.683	44.7	Blue NLF	1.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.06	93.23	0.180
89	R-4	7.616	0.683	44.7	Blue NLF	1.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.06	92.93	0.136
90	R-5	7.616	0.683	44.7	Blue NLF	1.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.06	92.43	0.137
91	S-1	7.616	0.683	44.7	Blue NLF	1.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.76	93.10	0.153
92	S-2	7.616	0.683	44.7	Blue NLF	1.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.76	96.27	0.145
93	S-3	7.616	0.683	44.7	Blue NLF	1.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.76	94.37	0.155
94	S-4	7.616	0.683	44.7	Blue NLF	1.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.76	93.03	0.140
95	S-5	7.616	0.683	44.7	Blue NLF	1.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.76	95.53	0.153
96	T-1	7.616	0.683	44.7	Blue NLF	1.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.51	93.53	0.155
97	T-2	7.616	0.683	44.7	Blue NLF	1.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.51	92.80	0.180
98	T-3	7.616	0.683	44.7	Blue NLF	1.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.51	93.00	0.148
99	T-4	7.616	0.683	44.7	Blue NLF	1.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.51	92.03	0.182
100	T-5	7.616	0.683	44.7	Blue NLF	1.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.19	60.51	92.47	0.148
101	U-1	7.616	0.683	44.7	Blue NLF	2.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.78	92.17	0.148
102	U-2	7.616	0.683	44.7	Blue NLF	2.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.78	94.80	0.140
103	U-3	7.616	0.683	44.7	Blue NLF	2.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.78	93.57	0.136
104	U-4	7.616	0.683	44.7	Blue NLF	2.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.78	92.27	0.137
105	U-5	7.616	0.683	44.7	Blue NLF	2.0	0.0	0.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.78	93.77	0.180
106	V-1	7.616	0.683	44.7	Blue NLF	2.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.33	92.50	0.180
107	V-2	7.616	0.683	44.7	Blue NLF	2.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.33	94.43	0.150
108	V-3	7.616	0.683	44.7	Blue NLF	2.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.33	94.37	0.162
109	V-4	7.616	0.683	44.7	Blue NLF	2.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.33	95.67	0.149
110	V-5	7.616	0.683	44.7	Blue NLF	2.0	2.0	1.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.33	93.53	0.146
111	W-1	7.616	0.683	44.7	Blue NLF	2.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.05	94.43	0.169
112	W-2	7.616	0.683	44.7	Blue NLF	2.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.05	93.00	0.154
113	W-3	7.616	0.683	44.7	Blue NLF	2.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.05	92.40	0.159
114	W-4	7.616	0.683	44.7	Blue NLF	2.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.05	95.00	0.154
115	W-5	7.616	0.683	44.7	Blue NLF	2.0	2.0	2.0	CF416	4	60	16493	0.095	60	360	5	91.44	60.05	96.37	0.145
116	X-1	7.616	0.683	44.7	Blue NLF	2.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.99	96.13	0.163
117	X-2	7.616	0.683	44.7	Blue NLF	2.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.99	93.13	0.179
118	X-3	7.616	0.683	44.7	Blue NLF	2.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.99	91.23	0.194
119	X-4	7.616	0.683	44.7	Blue NLF	2.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.99	91.33	0.194
120	X-5	7.616	0.683	44.7	Blue NLF	2.0	2.0	5.0	CF416	4	60	16493	0.095	60	360	5	91.44	59.99	87.57	0.199

BEST AVAILABLE COPY

To Page No. 47

Witnessed & Understood by me,

Date

Invented by

Date

Recorded by Kathy Weld

from Page No. 46

EXHIBIT E

Absorbent Product

1	A-1	76.06	84.05	-1.42	9.70	95.35	-1.38	9.93	78.37	94.78	-1.54	8.94	95.93	-1.49	8.09
2	A-2	74.98	83.88	-1.47	10.29	95.22	-1.43	10.58	77.68	94.85	-1.55	9.28	95.83	-1.50	9.48
3	A-3	78.33	94.25	-1.39	9.78	95.51	-1.35	9.99	79.28	94.93	-1.49	8.44	96.05	-1.44	8.58
4	A-4	78.27	94.14	-1.48	9.87	95.42	-1.43	9.90	78.87	94.92	-1.44	8.70	96.04	-1.39	8.84
5	A-5	78.11	94.05	-1.29	9.93	95.35	-1.25	9.88	77.39	94.56	-1.51	9.34	95.75	-1.48	9.52
6	B-1	80.22	95.82	-1.87	8.58	95.58	-1.81	8.79	82.63	96.74	-1.54	6.99	96.88	-1.48	7.00
7	B-2	80.59	95.59	-1.81	8.36	95.56	-1.75	8.44	83.02	95.88	-1.57	7.03	96.87	-1.51	7.04
8	B-3	80.89	95.89	-1.88	8.26	95.85	-1.80	8.33	82.94	95.88	-1.49	6.95	96.79	-1.43	6.96
9	B-4	80.42	95.55	-1.82	8.42	95.53	-1.88	8.51	82.59	95.95	-1.58	7.32	96.85	-1.53	7.35
10	B-5	79.48	95.27	-1.82	8.75	95.32	-1.88	8.87	82.35	95.74	-1.58	7.21	96.88	-1.53	7.23
11	C-1	81.43	96.74	-1.97	7.96	95.68	-1.90	8.01	83.69	95.99	-1.58	6.44	96.88	-1.82	6.44
12	C-2	81.57	95.88	-1.83	8.00	95.79	-1.88	8.08	84.82	96.32	-1.68	6.31	97.14	-1.80	8.29
13	C-3	80.30	95.74	-2.05	8.78	95.68	-1.98	8.88	83.18	96.12	-1.73	7.13	96.98	-1.87	7.14
14	C-4	80.72	95.81	-2.04	8.57	95.73	-1.98	8.68	84.34	96.15	-1.84	6.29	97.01	-1.49	8.27
15	C-5	80.91	95.84	-1.91	8.19	95.60	-1.85	8.27	83.65	95.99	-1.69	6.59	96.88	-1.83	6.58
16	D-1	82.80	96.15	-1.88	7.35	97.00	-1.79	7.38	86.50	96.58	-1.40	5.25	97.32	-1.25	5.19
17	D-2	81.97	95.88	-2.00	7.72	96.79	-1.93	7.77	86.76	96.80	-1.40	5.12	97.35	-1.34	5.08
18	D-3	81.83	95.88	-2.08	7.80	96.78	-2.01	7.85	86.16	96.53	-1.49	5.47	97.20	-1.43	5.43
19	D-4	83.21	96.18	-1.78	7.14	97.01	-1.72	7.15	88.79	96.55	-1.34	5.02	97.21	-1.29	4.98
20	D-5	82.29	96.07	-1.89	7.73	96.94	-1.81	7.78	88.23	96.40	-1.47	5.21	97.20	-1.42	5.18
21	E-1	75.83	93.10	-1.77	8.78	94.60	-1.73	8.88	78.78	93.55	-1.82	8.99	94.96	-1.48	7.07
22	E-2	76.07	92.84	-1.78	9.02	94.47	-1.74	9.25	77.98	93.58	-1.81	7.68	94.98	-1.78	7.79
23	E-3	78.79	93.01	-1.82	7.79	94.53	-1.58	7.93	80.38	93.81	-1.59	6.17	95.16	-1.54	6.20
24	E-4	74.71	92.53	-1.85	8.71	94.14	-1.81	8.83	77.63	93.34	-1.59	7.81	94.79	-1.54	7.72
25	E-5	75.57	92.70	-1.88	8.32	94.29	-1.82	8.50	77.44	93.24	-1.68	7.82	94.71	-1.83	7.74
26	F-1	79.59	93.25	-1.68	8.41	94.75	-1.61	8.48	81.12	93.63	-1.60	5.33	95.02	-1.45	5.34
27	F-2	78.20	93.27	-1.70	7.09	94.74	-1.85	7.17	80.39	93.70	-1.53	6.02	95.07	-1.48	6.04
28	F-3	78.92	93.40	-1.78	8.71	94.84	-1.71	8.77	80.31	93.69	-1.59	6.05	95.07	-1.55	6.08
29	F-4	79.02	93.18	-1.48	8.28	94.65	-1.45	8.33	82.01	93.83	-1.38	4.91	95.18	-1.32	4.90
30	F-5	78.68	93.33	-1.72	8.82	94.78	-1.67	8.89	81.34	93.79	-1.44	5.40	95.14	-1.40	5.41
31	G-1	82.29	95.57	-1.47	4.76	95.21	-1.43	4.76	84.38	94.37	-1.24	3.90	95.61	-1.20	3.88
32	G-2	80.72	93.84	-1.84	5.98	95.19	-1.59	5.98	83.77	94.38	-1.30	4.38	95.89	-1.28	4.33
33	G-3	81.41	93.82	-1.83	5.39	95.18	-1.49	5.39	84.09	94.30	-1.25	3.99	95.55	-1.21	3.96
34	G-4	82.56	93.59	-1.33	4.57	95.23	-1.29	4.55	85.15	94.38	-1.05	3.25	95.80	-1.02	3.21
35	G-5	79.88	93.69	-1.84	6.29	95.02	-1.50	6.34	83.61	94.25	-1.33	4.32	95.51	-1.29	4.30
36	H-1	82.56	94.23	-1.48	5.08	95.50	-1.44	5.08	85.57	94.78	-1.11	3.57	95.83	-1.07	3.52
37	H-2	82.42	94.13	-1.55	5.01	95.41	-1.50	4.99	85.01	94.81	-1.09	3.25	95.95	-1.05	3.21
38	H-3	83.38	94.28	-1.48	4.52	95.53	-1.41	4.50	85.87	94.72	-1.03	3.22	95.88	-0.99	3.18
39	H-4	82.84	94.21	-1.59	4.89	95.48	-1.54	4.95	85.14	94.67	-1.28	3.70	95.84	-1.22	3.66
40	H-5	82.68	94.20	-1.39	4.95	95.47	-1.35	4.94	86.47	94.79	-0.92	2.87	95.94	-0.88	2.82
41	I-1	79.59	92.99	-1.13	5.34	94.82	-1.10	5.38	81.14	93.17	-0.97	4.67	94.85	-0.94	4.66
42	I-2	77.25	92.05	-1.28	6.15	93.77	-1.23	6.23	79.10	92.48	-1.08	5.27	94.09	-1.05	5.29
43	I-3	76.93	91.92	-1.20	6.28	93.68	-1.17	6.34	78.51	92.04	-0.96	5.18	93.78	-0.94	5.19
44	I-4	78.14	91.50	-1.19	6.31	93.33	-1.17	6.40	77.81	91.83	-1.13	5.60	93.80	-1.11	5.65
45	I-5	78.37	91.22	-1.27	6.50	93.11	-1.25	6.61	76.92	91.68	-1.16	5.90	93.48	-1.13	5.97
46	J-1	78.57	91.88	-1.29	5.01	93.71	-1.28	5.05	81.11	92.27	-0.81	3.51	93.94	-0.88	3.49
47	J-2	78.62	91.77	-1.08	4.73	93.54	-1.08	4.78	80.49	92.14	-0.84	3.59	93.84	-0.82	3.63
48	J-3	78.78	91.78	-1.10	4.58	93.55	-1.08	4.81	80.08	92.12	-1.05	4.14	93.82	-1.03	4.14
49	J-4	78.71	91.33	-1.19	5.81	93.20	-1.16	5.85	78.62	91.93	-1.07	4.99	93.67	-1.05	5.02
50	J-5	79.27	91.88	-0.95	4.38	93.63	-0.92	4.37	80.30	92.15	-0.91	3.98	93.84	-0.89	3.96
51	K-1	77.13	91.76	-1.28	5.82	93.53	-1.25	5.98	80.53	92.18	-0.81	3.60	93.87	-0.78	3.59
52	K-2	77.80	91.68	-1.29	5.24	93.45	-1.27	5.28	79.43	92.10	-1.09	4.81	93.81	-1.06	4.83
53	K-3	80.21	92.15	-1.05	4.04	93.85	-1.03	4.04	81.45	92.41	-0.83	3.43	94.05	-0.81	3.42
54	K-4	77.02	91.93	-1.45	6.25	93.87	-1.42	6.33	80.91	92.38	-1.01	3.81	94.01	-0.99	3.80
55	K-5	78.21	91.87	-1.38	5.17	93.82	-1.35	5.20	81.40	92.47	-0.95	3.59	94.09	-0.93	3.58
56	L-1	80.87	92.29	-1.05	3.87	93.96	-1.05	3.88	84.70	92.94	-0.49	1.87	94.47	-0.47	1.86
57	L-2	81.25	92.40	-0.91	3.54	94.05	-0.89	3.82	84.27	92.94	-0.58	2.02	94.48	-0.56	1.99
58	L-3	80.84	92.51	-1.17	4.03	94.13	-1.14	4.02	84.30	92.95	-0.82	2.00	94.48	-0.80	1.97
59	L-4	81.28	92.34	-1.01	3.45	94.00	-0.98	3.44	85.08	92.81	-0.26	1.18	94.37	-0.94	1.16
60	L-5	78.48	92.14	-1.37	5.37	93.84	-1.34	5.42	83.63	92.56	-0.71	2.39	94.41	-0.69	2.36

BEST AVAILABLE COPY

To Page No. 48

Witnessed & Understood by me,

Date

Invented by

Date

Recorded by

Kathy Welch



## EXHIBIT F

		Minutes														
		0	1	2	3	4	5	6	7	8	9	10	11	12	13	14
61	M-1	77.56	94.46	-1.39	9.04	95.67	-1.35	9.21	79.28	94.80	-1.50	8.23	95.94	-1.45	8.34	
62	M-2	74.50	93.63	-1.43	10.32	95.02	-1.38	10.62	76.60	94.78	-1.65	8.74	96.93	-1.60	8.88	
63	M-3	76.03	94.22	-1.46	9.94	95.46	-1.42	10.19	78.20	94.80	-1.50	9.08	96.94	-1.45	9.24	
64	M-4	77.65	94.41	-1.38	8.95	95.64	-1.34	9.11	79.57	95.12	-1.49	8.23	96.19	-1.44	8.33	
65	M-5	76.96	94.25	-1.45	9.25	95.51	-1.40	9.45	79.33	94.98	-1.58	8.44	96.08	-1.53	8.66	
66	N-1	80.29	96.65	-1.87	8.47	96.63	-1.81	8.57	83.08	95.98	-1.73	7.01	96.88	-1.67	7.01	
67	N-2	79.80	95.32	-1.78	8.54	96.35	-1.72	8.85	83.20	95.81	-1.88	8.67	96.74	-1.82	8.67	
68	N-3	79.78	96.50	-2.09	8.80	96.49	-2.02	8.92	83.41	96.03	-1.78	6.82	96.91	-1.71	6.83	
69	N-4	78.73	95.19	-1.92	9.17	96.25	-1.88	9.32	81.68	95.49	-1.74	7.38	96.49	-1.68	7.42	
70	N-5	79.68	95.52	-1.94	8.94	96.51	-1.87	9.06	81.87	96.47	-1.77	7.20	96.48	-1.71	7.23	
71	O-1	80.78	95.67	-1.88	8.20	96.66	-1.81	8.29	84.91	96.11	-1.60	5.81	96.97	-1.54	5.79	
72	O-2	79.94	95.45	-1.91	8.83	96.46	-1.85	8.74	83.77	95.93	-1.73	8.39	96.83	-1.67	8.37	
73	O-3	81.65	95.86	-1.86	7.69	96.78	-1.80	7.94	84.82	95.96	-1.69	5.66	96.68	-1.63	5.63	
74	O-4	80.25	96.34	-2.03	8.29	96.37	-1.97	8.39	84.11	96.02	-1.66	8.28	96.90	-1.60	8.27	
75	O-5	80.84	95.78	-1.86	8.56	96.71	-1.80	8.67	83.91	96.13	-1.79	8.62	96.99	-1.72	8.61	
76	P-1	83.63	96.41	-1.91	7.04	97.20	-1.84	7.03	86.92	96.52	-1.41	4.87	97.30	-1.35	4.81	
77	P-2	82.76	96.10	-1.93	7.41	96.97	-1.88	7.43	86.77	96.27	-1.43	4.85	97.10	-1.37	4.80	
78	P-3	83.49	96.18	-1.97	7.01	97.02	-1.80	7.01	87.12	96.47	-1.32	4.94	97.28	-1.28	4.88	
79	P-4	83.81	96.17	-1.98	6.92	97.02	-1.89	6.92	87.05	96.34	-1.32	4.84	97.15	-1.28	4.68	
80	P-5	84.81	96.40	-1.82	6.31	97.20	-1.76	6.29	87.09	96.48	-1.27	4.66	97.25	-1.22	4.60	
81	Q-1	77.55	94.62	-2.27	9.33	96.80	-2.21	9.51	81.99	95.29	-1.67	6.67	96.33	-1.60	6.69	
82	Q-2	76.77	94.15	-1.93	10.08	95.43	-1.88	10.34	79.12	94.80	-1.63	8.07	95.79	-1.77	8.17	
83	Q-3	77.10	94.38	-1.81	9.36	95.61	-1.76	9.58	79.82	94.76	-1.78	7.81	95.90	-1.72	7.69	
84	Q-4	76.16	94.12	-1.82	9.71	95.41	-1.77	9.94	78.53	94.67	-1.85	8.66	95.84	-1.80	8.78	
85	Q-5	76.43	94.20	-1.74	9.80	95.47	-1.69	9.81	78.84	94.70	-1.82	8.43	95.86	-1.77	8.68	
86	R-1	78.22	94.76	-2.14												

Recorded by

## EXHIBIT G

### Absorbent Product

1	A-1	78.07	94.86	-1.75	9.25	95.99	-1.69	9.42	79.59	95.22	-1.55	8.58	96.28	-1.50	8.69
2	A-2	77.62	94.62	-1.70	9.29	95.80	-1.65	9.47	78.39	94.98	-1.57	9.20	96.10	-1.52	8.36
3	A-3	79.48	94.97	-1.60	8.29	96.08	-1.56	8.40	79.09	95.00	-1.58	8.64	96.10	-1.53	8.76
4	A-4	79.48	95.06	-1.61	8.47	96.14	-1.56	8.58	78.54	95.12	-1.79	8.25	96.19	-1.73	9.41
5	A-5	77.74	94.78	-1.56	9.35	95.93	-1.63	9.53	78.16	95.00	-1.64	9.36	96.10	-1.59	9.53
6	B-1	83.82	95.98	-1.61	6.43	96.87	-1.56	6.42	83.10	96.90	-1.80	6.80	96.80	-1.55	6.81
7	B-2	83.21	95.96	-1.79	6.88	96.85	-1.72	6.88	83.51	96.01	-1.69	6.71	96.89	-1.62	6.71
8	B-3	84.10	96.05	-1.68	6.32	96.92	-1.62	6.30	82.67	96.03	-1.81	7.45	96.91	-1.75	7.48
9	B-4	83.37	95.92	-1.67	6.72	96.82	-1.61	6.72	82.98	95.89	-1.85	6.97	96.80	-1.78	6.98
10	B-5	83.51	96.07	-1.68	6.76	96.94	-1.60	6.76	83.13	96.11	-1.72	7.13	96.97	-1.65	7.15
11	C-1	84.23	95.52	-1.58	5.48	96.51	-1.52	5.45	84.40	95.53	-1.83	5.28	97.30	-1.56	5.23
12	C-2	85.13	96.20	-1.75	5.78	97.05	-1.68	5.72	85.68	96.56	-1.86	5.89	97.32	-1.80	5.85
13	C-3	84.85	96.21	-1.72	6.14	97.06	-1.66	6.12	84.04	96.21	-1.86	6.86	97.05	-1.80	6.55
14	C-4	84.87	96.26	-1.74	6.17	97.08	-1.67	6.14	84.74	96.32	-1.80	6.28	97.14	-1.73	6.28
15	C-5	84.97	96.02	-1.61	5.65	96.90	-1.55	5.61	85.44	96.43	-1.61	5.84	97.22	-1.55	5.80
16	D-1	87.80	96.50	-1.36	4.36	97.28	-1.31	4.29	88.63	96.76	-1.28	3.89	97.47	-1.21	3.82
17	D-2	88.82	96.88	-1.58	5.14	97.40	-1.52	5.08	88.28	96.88	-1.38	4.34	97.58	-1.33	4.27
18	D-3	88.88	96.65	-1.60	5.11	97.38	-1.54	5.05	87.21	96.45	-1.54	4.80	97.22	-1.48	4.54
19	D-4	87.58	96.65	-1.35	4.41	97.32	-1.29	4.36	88.16	96.49	-1.34	3.91	97.28	-1.29	3.85
20	D-5	88.76	96.40	-1.54	4.84	97.20	-1.48	4.79	87.10	96.58	-1.45	4.77	97.33	-1.40	4.71
21	E-1	81.48	94.05	-1.48	5.82	95.35	-1.41	5.63	82.10	94.04	-1.34	5.12	95.35	-1.30	5.11
22	E-2	79.90	93.70	-1.68	6.38	95.08	-1.61	6.40	79.74	93.74	-1.62	6.53	95.11	-1.58	6.56
23	E-3	81.86	93.78	-1.24	4.93	95.14	-1.20	4.92	82.38	93.81	-1.16	4.58	95.18	-1.12	4.58
24	E-4	78.78	93.41	-1.52	6.84	94.85	-1.48	6.91	78.65	93.33	-1.55	6.57	94.78	-1.50	6.95
25	E-5	78.26	93.23	-1.70	6.94	94.70	-1.69	7.03	79.33	93.45	-1.58	6.44	94.88	-1.53	6.49
26	F-1	82.40	93.76	-1.35	4.55	95.13	-1.31	4.53	83.78	93.78	-1.14	3.49	95.14	-1.11	3.48
27	F-2	81.22	93.67	-1.61	5.34	95.05	-1.47	5.35	82.17	93.75	-1.33	4.69	95.12	-1.29	4.67
28	F-3	82.20	93.68	-1.38	4.88	95.22	-1.32	4.88	82.86	93.94	-1.34	4.60	95.27	-1.30	4.58
29	F-4	83.42	93.53	-1.09	3.63	95.17	-1.05	3.60	83.73	93.87	-1.08	3.66	95.21	-1.05	3.62
30	F-5	81.87	93.62	-1.28	4.62	95.01	-1.24	4.61	82.60	93.73	-1.22	4.42	95.10	-1.18	4.40
31	G-1	85.10	94.33	-0.88	2.80	95.58	-0.85	2.48	86.47	94.48	-0.93	2.38	95.67	-0.90	2.34
32	G-2	85.30	94.40	-0.92	2.44	95.63	-0.88	2.41	86.43	94.53	-0.88	2.49	95.73	-0.85	2.44
33	G-3	85.87	94.44	-0.93	2.74	95.88	-0.89	2.70	86.43	94.47	-0.94	2.45	95.89	-0.91	2.41
34	G-4	86.28	94.30	-0.84	2.29	95.56	-0.81	2.25	86.81	94.52	-0.88	2.37	95.72	-0.85	2.33
35	G-5	86.26	94.27	-1.08	3.02	95.53	-1.04	2.98	86.54	94.52	-0.88	2.42	95.72	-0.84	2.38
36	H-1	87.79	94.73	-0.47	1.69	95.89	-0.45	1.65	88.50	95.16	-0.68	1.80	96.28	-0.63	1.78
37	H-2	88.04	94.92	-0.49	1.77	96.04	-0.47	1.73	88.11	95.12	-0.82	2.04	96.20	-0.79	2.00
38	H-3	87.83	94.78	-0.51	1.87	95.93	-0.49	1.83	88.31	95.11	-0.73	1.87	96.18	-0.70	1.83
39	H-4	87.82	94.82	-0.49	1.78	95.96	-0.46	1.69	86.77	95.08	-0.61	1.44	96.14	-0.59	1.40
40	H-5	88.22	94.93	-0.42	1.63	96.04	-0.40	1.59	86.67	95.16	-0.64	1.41	96.22	-0.52	1.37
41	I-1	82.82	93.28	-0.69	3.51	94.76	-0.67	3.49	81.48	92.89	-0.88	4.02	94.44	-0.85	4.01
42	I-2	81.56	92.68	-0.73	3.68	94.27	-0.71	3.84	80.80	92.48	-0.91	4.11	94.11	-0.88	4.10
43	I-3	81.11	92.18	-0.67	3.46	93.95	-0.84	3.44	79.77	92.81	-0.98	4.55	93.96	-0.95	4.56
44	I-4	80.97	92.29	-0.64	3.45	93.88	-0.82	3.44	79.44	92.00	-0.97	4.40	93.73	-0.94	4.42
45	I-5	80.22	91.96	-0.65	3.72	93.70	-0.83	3.72	79.12	91.78	-0.87	4.29	93.68	-0.85	4.30
46	J-1	83.83	92.26	-0.39	2.07	93.53	-0.38	2.05	81.90	92.27	-0.79	2.87	93.94	-0.76	2.85
47	J-2	83.05	92.29	-0.35	1.97	93.96	-0.33	1.94	80.85	92.02	-0.83	3.47	93.74	-0.80	3.46
48	J-3	81.57	92.09	-0.55	2.74	93.76	-0.63	2.72	81.88	92.27	-0.85	3.07	93.94	-0.83	3.05
49	J-4	81.92	92.09	-0.47	2.47	93.75	-0.45	2.45	80.89	92.08	-0.77	3.53	93.79	-0.74	3.53
50	J-5	83.07	92.26	-0.26	1.87	93.93	-0.25	1.85	81.10	92.20	-0.78	3.40	93.88	-0.74	3.39
51	K-1	83.74	92.44	-0.27	1.84	94.08	-0.28	1.81	83.78	92.65	-0.45	1.81	94.17	-0.43	1.78
52	K-2	82.44	92.24	-0.51	2.38	93.92	-0.50	2.35	81.71	92.23	-0.72	2.99	93.91	-0.70	2.97
53	K-3	83.65	92.25	-0.28	1.50	93.92	-0.27	1.47	84.48	92.86	-0.43	1.71	94.41	-0.41	1.69
54	K-4	83.92	92.46	-0.29	1.49	94.09	-0.28	1.47	84.02	92.82	-0.65	2.02	94.38	-0.63	1.99
55	K-5	84.43	92.53	-0.18	1.21	94.15	-0.17	1.19	84.83	92.85	-0.43	1.41	94.40	-0.42	1.39
56	L-1	86.72	93.06	0.09	0.18	94.57	0.09	0.18	87.21	93.57	-0.27	0.71	95.05	-0.28	0.69
57	L-2	86.64	93.12	0.09	0.18	94.62	0.09	0.18	87.85	93.45	0.01	-0.16	94.55	0.02	-0.18
58	L-3	86.93	93.20	0.06	0.28	94.68	0.06	0.28	87.73	93.44	0.05	-0.07	94.87	0.06	-0.07
59	L-4	86.94	93.04	0.12	0.01	94.55	0.13	0.01	87.43	93.49	-0.09	0.22	94.91	-0.02	0.22
60	L-5	86.91	92.97	-0.12	0.71	94.60	-0.11	0.70	87.15	93.54	-0.12	0.62	94.94	-0.11	0.51

**BEST AVAILABLE COPY**

To Page No. 50

**Witnessed & Understood by me,**

Date \_\_\_\_\_

Invented by

Date \_\_\_\_\_

Recorded by

Kathy Welch

## EXHIBIT H

61	M-1	79.41	95.19	-1.69	8.67	96.25	-1.64	8.78	79.62	95.08	-1.43	8.35	96.17	-1.38	8.45
62	M-2	79.77	95.33	-1.69	8.57	96.38	-1.64	8.67	80.43	95.35	-1.45	8.11	96.37	-1.40	8.20
63	M-3	80.84	95.48	-1.62	8.15	96.48	-1.56	8.23	78.70	95.05	-1.57	9.00	96.14	-1.52	9.15
64	M-4	80.36	95.28	-1.77	8.05	96.32	-1.71	8.13	80.95	95.41	-1.44	7.79	96.43	-1.39	7.85
65	M-5	80.46	95.45	-1.54	8.22	96.45	-1.48	8.31	80.11	95.11	-1.40	8.01	96.19	-1.35	8.09
66	N-1	84.23	96.17	-1.92	6.43	97.02	-1.95	6.42	84.57	96.07	-1.65	6.00	96.94	-1.59	6.58
67	N-2	84.91	96.27	-1.70	6.01	97.10	-1.64	5.98	84.20	96.21	-1.79	6.50	97.05	-1.72	6.45
68	N-3	84.07	96.16	-1.77	6.50	97.01	-1.70	6.49	84.25	96.18	-1.69	6.40	97.03	-1.63	6.38
69	N-4	82.03	96.74	-2.08	7.51	96.88	-2.01	7.55	83.06	96.72	-1.75	6.89	96.67	-1.69	6.70
70	N-5	83.44	96.01	-1.83	6.79	96.89	-1.77	6.79	82.77	95.60	-1.70	7.03	96.73	-1.64	7.04
71	O-1	87.72	96.85	-1.28	4.45	97.39	-1.23	4.38	88.58	96.48	-1.53	6.10	97.28	-1.47	6.05
72	O-2	86.38	96.14	-1.73	5.54	97.00	-1.67	5.60	85.45	96.06	-1.63	5.38	96.95	-1.57	5.34
73	O-3	85.80	96.23	-1.77	5.47	97.15	-1.71	5.42	85.83	96.44	-1.49	4.82	97.23	-1.43	4.78
74	O-4	84.85	95.98	-1.66	5.65	96.88	-1.60	5.61	85.29	96.39	-1.54	5.90	97.19	-1.48	5.87
75	O-5	85.40	96.34	-1.62	5.78	97.15	-1.57	5.72	85.27	96.34	-1.73	5.58	97.16	-1.66	5.54
76	P-1	88.82	96.69	-1.27	3.68	97.43	-1.22	3.61	89.23	96.75	-1.24	3.48	97.47	-1.19	3.41
77	P-2	88.13	96.56	-1.39	4.00	97.32	-1.34	3.93	89.03	96.82	-1.21	3.70	97.53	-1.16	3.63
78	P-3	88.28	96.39	-1.24	3.86	97.19	-1.19	3.59	89.22	96.84	-1.10	3.58	97.54	-1.05	3.51
79	P-4	88.43	96.96	-1.34	4.38	97.84	-1.29	4.29	88.50	96.68	-1.25	3.91	97.42	-1.20	3.84
80	P-5	88.46	96.78	-1.40	4.08	97.48	-1.34	4.01	88.86	96.70	-1.28	3.97	97.43	-1.23	3.80
81	Q-1	83.32	95.59	-1.71	6.30	96.57	-1.66	6.29	84.18	95.37	-1.73	5.38	96.39	-1.67	5.33
82	Q-2	79.81	94.90	-1.89	8.18	96.02	-1.83	8.28	80.00	94.94	-1.78	7.94	96.06	-1.72	8.03
83	Q-3	80.62	95.06	-1.92	7.58	96.14	-1.86	7.64	80.16	94.91	-1.88	7.78	96.02	-1.82	7.84
84	Q-4	81.25	94.99	-1.64	7.00	96.09	-1.49	7.04	79.40	94.87	-1.82	8.29	96.02	-1.86	8.49
85	Q-5	81.52	95.08	-1.62	6.50	96.16	-1.47	6.83	79.47	94.87	-1.88	8.23	96.00	-1.82	8.33
86	R-1	83.94	95.48	-1.60	5.69	96.48	-1.55	5.64	82.48	96.40	-1.79	6.58	96.41	-1.73	6.70
87	R-2	84.05	95.58	-1.56	5.71	96.53	-1.51	5.69	83.00	95.56	-1.90	6.83	96.54	-1.84	6.53
88	R-3	85.46	95.57	-1.33	4.60	96.55	-1.28	4.65	84.84	95.65	-1.68	6.39	96.61	-1.61	6.36
89	R-4	84.85	95.54	-1.43	5.07	96.53	-1.38	5.04	85.00	95.77	-1.68	6.31	96.71	-1.60	6.27
90	R-5	83.68	95.48	-1.57	5.87	96.47	-1.51	5.85	83.93	95.65	-1.69	6.92	96.61	-1.63	6.90
91	S-1	85.30	95.75	-1.54	5.04	96.70	-1.49	4.99	86.51	95.58	-1.47	4.28	96.78	-1.42	4.23
92	S-2	86.06	95.92	-1.42	4.69	96.83	-1.37	4.63	86.82	96.01	-1.51	4.42	96.89	-1.48	4.38
93	S-3	86.10	96.02	-1.34	4.77	96.90	-1.29	4.72	86.27	95.95	-1.51	4.58	96.85	-1.45	4.53
94	S-4	85.08	96.08	-1.58	4.92	96.95	-1.50	4.87	85.38	95.74	-1.60	4.93	96.88	-1.54	4.89
95	S-5	84.55	95.98	-1.49	5.41	96.82	-1.43	5.37	84.80	95.82	-1.59	5.49	96.74	-1.53	5.45
96	T-1	88.50	96.31	-1.11	3.33	97.13	-1.06	3.27	89.34	96.24	-1.00	2.64	97.08	-0.98	2.58
97	T-2	88.59	96.19	-1.04	3.11	97.04	-1.00	3.05	89.12	96.30	-1.07	2.90	97.12	-1.02	2.84
98	T-3	88.75	96.42	-1.08	3.31	97.21	-1.01	3.25	88.91	96.11	-1.08	2.81	96.98	-1.03	2.75
99	T-4	89.11	96.42	-0.98	3.05	97.21	-0.93	2.99	88.90	96.40	-1.20	3.24	97.20	-1.16	3.17
100	T-5	88.33	96.32	-1.13	3.51	97.14	-1.08	3.45	88.77	96.38	-1.28	3.33	97.18	-1.23	3.28
101	U-1	81.92	94.40	-1.78	5.72	95.83	-1.73	5.73	82.01	94.50	-1.92	5.82	95.71	-1.86	5.82
102	U-2	81.33	94.60	-1.65	6.47	95.78	-1.79	6.50	80.11	94.32	-1.91	6.96	95.56	-1.85	7.03
103	U-3	80.70	94.27	-1.78	6.44	95.53	-1.73	6.47	78.06	93.81	-2.03	7.66	95.16	-1.98	7.87
104	U-4	81.19	94.34	-1.72	6.17	95.58	-1.67	6.19	80.16	94.35	-2.07	7.01	95.89	-2.01	7.08
105	U-5	81.95	94.44	-1.69	6.77	95.68	-1.64	6.77	80.30	94.30	-1.57	6.53	95.55	-1.51	6.58
106	V-1	84.82	95.15	-1.48	4.48	96.22	-1.43	4.44	84.97	95.19	-1.64	4.81	96.28	-1.58	4.47
107	V-2	84.74	95.02	-1.43	4.41	96.12	-1.38	4.37	83.80	95.09	-1.73	5.27	96.17	-1.67	5.24
108	V-3	85.43	95.12	-1.38	4.03	96.20	-1.31	3.98	85.81	95.17	-1.49	3.98	96.24	-1.44	3.93
109	V-4	84.48	94.97	-1.42	4.54	96.08	-1.38	4.51	82.73	94.88	-1.63	5.78	95.98	-1.78	5.75
110	V-5	83.79	94.89	-1.63	5.02	96.04	-1.48	5.00	82.03	94.77	-1.83	6.15	95.91	-1.77	6.17
111	W-1	86.67	95.47	-1.23	3.40	96.48	-1.18	3.34	87.45	95.64	-1.23	3.24	96.60	-1.19	3.19
112	W-2	86.03	95.40	-1.39	3.97	96.41	-1.34	3.92	86.78	95.40	-1.34	3.43	96.41	-1.29	3.37
113	W-3	86.67	95.31	-1.14	3.19	96.35	-1.10	3.14	86.20	95.42	-1.54	3.94	96.43	-1.48	3.89
114	W-4	86.68	95.42	-1.31	3.62	96.43	-1.26	3.46	86.08	95.41	-1.47	3.96	96.42	-1.42	3.91
115	W-5	85.00	95.13	-1.42	4.40	96.20	-1.37	4.35	84.19	95.15	-1.64	5.05	96.22	-1.58	5.01
116	X-1	88.15	95.78	-1.12	2.90	96.72	-1.07	2.85	88.12	95.74	-1.21	2.88	96.68	-1.16	2.83
117	X-2	88.71	95.66	-0.94	2.27	96.62	-0.90	2.22	88.17	95.73	-0.91	2.02	96.67	-0.87	1.97
118	X-3	89.01	95.80	-1.02	2.24	96.73	-0.98	2.19	88.48	95.84	-0.97	1.97	96.77	-0.93	1.92
119	X-4	89.21	95.88	-0.96	2.22	96.80	-0.92	2.17	89.28	95.81	-1.00	2.08	96.74	-0.98	2.02
120	X-5	89.03	95.78	-1.07	2.22	96.72	-1.03	2.17	89.31	95.81	-1.18	2.04	96.74	-1.12	1.99

## % Consistency Results - Pulp Feed

## Absorbent Products Pilot Line - Trial # 81

Operator: Kathy

Date: [REDACTED]

PF-11	10.28	11.07	92.88	9.47	10.21	92.75	8.48	9.12	92.78	92.79	92.55
PF-1t	10.35	11.24	92.08	9.69	10.48	92.48	9.20	9.98	92.37	92.30	
PF-21	10.52	11.40	92.28	9.07	9.81	92.48	9.33	10.09	92.47	92.40	92.34
PF-2t	11.67	12.65	92.25	9.48	10.24	92.38	10.19	11.05	92.22	92.28	
PF-31	10.25	11.11	92.25	9.34	10.13	92.20	9.34	10.11	92.38	92.28	91.70
PF-3t	9.91	10.88	91.08	10.34	11.35	91.10	9.70	10.64	91.17	91.12	
PF-41	9.71	10.58	91.95	9.47	10.30	91.94	9.79	10.63	92.10	92.00	92.42
PF-4t	8.19	8.84	92.65	8.57	9.24	92.75	8.02	8.61	93.15	92.85	
PF-51 (Day 1)	9.84	10.67	92.22	8.81	9.55	92.25	9.20	9.98	92.37	92.28	92.40
PF-5t (Day 1)	9.50	10.27	92.50	10.02	10.83	92.52	9.20	9.94	92.56	92.53	
PF-51 (Day 2)	9.48	10.42	90.79	8.89	9.79	90.81	8.91	9.81	90.83	90.81	91.21
PF-5t (Day 2)	9.43	10.30	91.55	9.09	10.90	91.65	8.90	9.71	91.68	91.62	
PF-61	9.02	9.84	91.67	9.00	9.80	91.84	8.81	9.59	91.87	91.79	91.31
PF-6t	8.86	9.78	90.78	8.58	9.45	90.79	9.32	10.25	90.93	90.83	
PF-71	9.68	10.64	90.98	9.23	10.15	90.94	9.64	10.63	90.69	90.87	91.19
PF-7t	10.23	11.20	91.34	9.05	9.88	91.60	9.59	10.47	91.60	91.51	
PF-81	8.82	9.43	91.41	8.91	9.74	91.48	9.99	10.90	91.65	91.51	91.44
PF-8t	9.23	10.10	91.39	9.14	9.99	91.49	9.67	10.60	91.23	91.37	
PF-91	9.68	10.62	91.15	8.99	9.84	91.38	8.78	9.61	91.36	91.29	91.78
PF-9t	10.14	10.99	92.27	9.32	10.08	92.48	9.89	10.74	92.09	92.27	